



NA2XS(F)2Y 6/10 (12)kV Cable



Eland Product Group: A9X

APPLICATION

Medium voltage power cables with additional waterblocking properties for distribution networks and generation units, suitable for external installation including in direct in ground and in buried cable ducts. UV Resistant.

CHARACTERISTICS

Voltage Rating U_o/U (Um)
6/10 (12)kV

Test Voltage
21kV AC 50Hz (5 mins)

Temperature Rating
-20°C to +60°C
Permissible Conductor Operating Temperature: +90°C
Permissible Short Circuit Temperature up to 5 sec: 250°C

Minimum Bending Radius
15 x overall diameter

CONSTRUCTION

Conductor
Class 2 Stranded Aluminium

Conductor Screen
Semi-conductive material

Insulation
XLPE (Cross-Linked Polyethylene)

Insulation Screen
Semi-conductive material (bonded)

Longitudinal Waterblocking
Semi-conductive swellable tape

Screen
Copper wires and copper tape

Longitudinal Waterblocking
Swellable Tapes

Outer Sheath
MDPE (Medium Density Polyethylene)

Sheath Colour
● Red ● Black

STANDARDS

IEC 60502-2, IEC 60228,
UV Resistant: ISO 4892-3
Abrasion and Tear Resistant: EN 60229-4.1
Impact rated to: AG2 EN 60364-5.51

THE CABLE LAB[®]

AN ISO/IEC 17025 AND IECIE CBTB ACCREDITED FACILITY

Our world-class testing facility assures the quality and compliance of this cable through a continuous and rigorous testing regime.



SUSTAINABILITY COMMITMENT

We are on a journey to Net Zero.

We've committed to near-term emissions reductions and a net-zero target with the Science Based Targets initiative and we're a signatory to the United Nations Global Compact Sustainable Development Goals.

Learn more about embodied carbon and our carbon emissions reduction actions, our comprehensive recycling services, and wider ESG activities for sustainable operations at: www.elandcables.com/company/about-us/esg-sustainability



REGULATORY COMPLIANCE

This cable meets the requirements of the RoHS Directive 2015/65/EU and Reach Directive EC 1907/2006. RoHS compliance has been tested and confirmed by The Cable Lab[®].





DIMENSIONS

ELAND PART NO.	NO. OF CORES	NOMINAL CROSS SECTIONAL AREA mm ²		NOMINAL CONDUCTOR DIAMETER mm	NUMBER WIRES CONDUCTOR mm	NOM. THICKNESS SEMI-CON. LAYER		NOMINAL INSULATION THICKNESS mm	MINIMUM INSULATION THICKNESS mm	NOMINAL DIAMETER OVER INSULATION mm
		Conductor	Screen			INNER mm	OUTER mm			
A9XAF10KV1050	1	50	16	8.20	7 x 2.90	0.50	0.40	3.40	2.96	16.4
A9XAF10KV1070	1	70	16	9.70	19 x 2.18	0.50	0.40	3.40	2.96	17.9
A9XAF10KV1095	1	95	16	11.4	19 x 2.55	0.50	0.40	3.40	2.96	19.6
A9XAF10KV1120	1	120	16	12.65	19 x 2.90	0.50	0.40	3.40	2.96	20.9
A9XAF10KV1150	1	150	25	14.4	19 x 3.16	0.50	0.40	3.40	2.96	22.6
A9XAF10KV1185	1	185	25	15.75	37 x 2.55	0.50	0.40	3.40	2.96	24.4
A9XAF10KV1240	1	240	25	18.2	37 x 2.90	0.50	0.40	3.40	2.96	26.9
A9XAF10KV1300	1	300	25	20.5	61 x 2.55	0.50	0.40	3.40	2.96	29.2
A9XAF10KV1400	1	400	35	23.0	61 x 2.90	0.50	0.40	3.40	2.96	31.7
A9XAF10KV1500	1	500	35	26.0	61 x 3.20	0.50	0.40	3.40	2.96	34.7
A9XAF10KV1630	1	630	35	30.2	61 x 3.65	0.50	0.40	3.40	2.96	38.9

NOMINAL CROSS SECTIONAL AREA mm ²	NUMBER WIRES SCREEN mm	DIAMETER TAPE SCREEN mm	NOMINAL SHEATH THICKNESS mm	MINIMUM SHEATH THICKNESS mm	NOMINAL OVERALL DIAMETER mm	NOMINAL WEIGHT kg/km	MAXIMUM SIDEWALL PRESSURE N/cm ²	MAXIMUM PULLING TENSION N
50	44 x 0.66	1x0.1x10	1.80	1.24	23	550	331	1500
70	44 x 0.66	1x0.1x10	1.80	1.24	24	650	415	2100
95	44 x 0.66	1x0.1x10	1.80	1.24	26	750	522	2850
120	44 x 0.66	1x0.1x10	1.80	1.24	27	850	621	4500
150	71 x 0.66	1x0.1x10	1.90	1.32	29	1100	708	7500
185	71 x 0.66	1x0.1x10	1.90	1.32	31	1200	809	5550
240	71 x 0.66	1x0.1x10	2.00	1.40	33	1400	938	7200
300	71 x 0.66	1x0.1x10	2.10	1.48	36	1600	1081	9000
400	60 x 0.85	1x0.1x15	2.20	1.56	39	2000	1311	12000
500	60 x 0.85	1x0.1x15	2.30	1.64	42	2500	1471	15000
630	60 x 0.85	1x0.1x15	2.40	1.72	46	3000	1654	18900



ELECTRICAL CHARACTERISTICS

NOMINAL CROSS SECTIONAL AREA mm ²	CONDUCTOR DC RESISTANCE AT 20°C	CONDUCTOR DC RESISTANCE AT 75°C	CONDUCTOR AC RESISTANCE BY MAX TEMP	CURRENT CARRYING CAPACITY (A)		REACTANCE	CHARGING ADMITTANCE	CAPACITANCE	S.C.C CONDUCTOR 1SEC kA	S.C.C SCREEN 1SEC kA	CONDUCTOR LOSSES IN THE GROUND
	ohms/km	ohms/km	ohms/km	In Ground 20°C	In Air 30°C	ohms/km	A/km	uF/km		kA	kW/km
50	0.641	1.32	0.825	194	215	0.18	0.35	0.22	4.70	3.2	31.0
70	0.443	0.917	0.570	236	269	0.17	0.33	0.24	6.58	3.2	31.7
95	0.32	0.662	0.412	281	327	0.17	0.32	0.28	8.93	3.2	32.5
120	0.258	0.524	0.328	318	377	0.16	0.31	0.30	11.28	3.2	33.2
150	0.203	0.426	0.268	350	424	0.16	0.30	0.33	14.10	5.0	32.8
185	0.165	0.339	0.213	393	485	0.16	0.29	0.36	17.39	5.0	32.9
240	0.125	0.258	0.160	453	573	0.15	0.28	0.40	22.56	5.0	33.4
300	0.100	0.207	0.132	507	652	0.15	0.28	0.45	28.20	5.0	33.9
400	0.0778	0.161	0.103	559	741	0.15	0.27	0.49	37.60	7.1	32.2
500	0.0605	0.125	0.0810	622	838	0.15	0.26	0.54	47.00	7.1	31.3
630	0.0469	0.0972	0.0640	860	1080	0.14	0.25	0.62	59.22	7.1	47.3

Derating factor (ground): 1 (Soil thermal resistivity: 1km/W, Depth 0.8m, Flat formation - touching)

Derating factor (air): 1 (Flat formation - touching)